

GRAPHICS - RI-MARK

Issue date : 23/03/2009
Date last modification : 13/12/2016**4-GL3C-05126 ETCH GLASS PTA AIRFLOW SILVER TRANSLUCENT ASP26
PERMANENT WKPE160****Face Material**

Self-adhesive material for plotter. Polymeric translucent vinyl with silver metallic flakes.

Type	Polymeric vinyl with metallic flakes	
Colour and Finish	Silver translucent	
Weight	100 g/m ² ±10%	ISO-536
Thickness	80 µ ±10%	ISO 534-80

Adhesive

Solvent based acrylic permanent adhesive featuring high cohesion. The excellent water resistance allows wet application of the material. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	ASP26 with airflow liner	
Type	Permanent acrylic	
Min. Appl. Temp.	+10°C	
Service Temp.	-20°C/+130°C	
Shear	High	
Tack	Medium N/25mm	FINAT FTM9
Final Adhesion	High N/25mm	FINAT FTM2

Liner

Type	Embossed PE coated Kraft paper	
Colour and Finish	White	
Weight	160 g/m ² ±10%	PP-032 - ISO 536
Thickness	190 µ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

Applications

A special pattern in the adhesive coating allows trapped air to be easily eliminated through special channels ensuring accurate trouble-free and fast applications. It allows clean removal from the glass at the end of the graphic's life. The use of water is not recommended. Suitable for 5 years etch glass outdoor applications. Size available: h 1220/1520 mm; length 50 m.

Printing Methods

Not printable.
Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

